wherein either one of the sheets contains activated carbon and the other has a deodorising function caused by chemical reaction or catalytic action.

Chemicals to be used for deodorisation by chemical r action are phosphoric acid, sulphuric acid, citric acid, ascorbic acid for basic gas, and cupric phosphate, copper iodide, ferrous sulphate, zinc oxide for both acidic and basic gases. The catalysts for decomposing odour are palladium chloride, silver chloride, etc.. Materials for electret filter are, e.g. polyethylene, polypropylene, polyester, polyvinyl fluoride. USE/ADVANTAGE - The present filter is used for removing floating dust and odour in the air, esp. in rooms and cars. The present filter can remove very small dust (less than 1 micron), and also remove odour not adsorbed by the activated carbon, by the chemical reaction or catalytic decompsn.. (Dwg.0/3)

-9-(WPAT) - 89-127716/17 AN XRAM- C89-056791 XRPX- N89-097301 - Low pressure loss air cleaner - comprises electret filter to collect dust and honeycomb catalyst to adsorb odours (J5.14.10.83)- D22 J01 P34 (TOYM ) TOYOBO KK 82.04.08 82JP-059284 NUM - 2 patent(s) 1 country(s) PN -- JP89017378 B 89.03.30 \* (8917) 2p - JP58175560 A AP -- 82JP-059284 83.10.14 (8917) 82.04.08 IC2 - A61L-009/16 B01D-039/14 B01D-053/00 - JP89017378 B

Air cleaner of low pressure loss type comprises an electret filter to collect the dust flying in the air and honeycomb type sheet-like catalyst pieces combined with the filter, to adsorb malodorous components of the air.

USE - Used for rooms of houses and vehicles.

AN - 85-034895/06 XRAM- C85-015111 XRPX- N85-025806 TI - Electret honeycomb filter - has honeycomb cells with sides of opposite polarity DC - A18 A88 J01 P41 PA - (XERF ) FUJI XEROX CO LTD PR - 83.06.09 83JP-101800 NUM - 1 patent(s) 1 country(s) PN -- JP59228919 A 84.12.22 \* (8506) AP -- 83JP-101800 83.06.09 IC2 - B01D-039/16 B03C-003/28 - JP59228919 A AΒ

-10-

(WPAT)

Electret honeycomb filter is composed of an electret film in a honeycomb structure in such a manner that the inner wall of each honeycomb cell is formed as a positive polarity face at one side and as a negative polarity face at the other side.

An electroconductive substance is vapour deposited on one of the opposite surfaces of a sh et of perfluoroalkoxy (PFA) or fluoro-ethyl n -propylene (FEP) having an 1 ctr t property, in a thickness of about 10-50 micron and corona radiation of ion beam radiation is performed from non-deposited surface. The electret sheets ar heaped upon ach oth r at a specific interval, and bonded in a hon ycomb fashion by means of an adhesive to give the electret honeycomb filt r.

ADVANTAGE - Extremely high particle collecting ability and capacity can be obtd. with a low pressur loss and reduction in weight. (0/5)

\$5

## ① 日本国特許庁 (JP)

10 特許出願公開

# ⑫公開特許公報(A)

昭58—175560

DInt. Cl.3

識別記号

庁内整理番号

❸公開 昭和58年(1983)10月14日

A 61 L 9/16 B 01 D 39/14 53/04

6917-4C 6425-4D 7917-4D

発明の数 1 審査請求 未請求

(全 3 頁)

### **9**空気清浄機

20特

昭57-59284

22出

昭57(1982) 4月8日

@発 明 者 大森進 岡山市西大寺南2丁目10の37

加出 願 人 東洋紡績株式会社

大阪市北区堂島浜2丁目2番8

号

#### 発明の名称

空気滑浄傷

#### 特許維求の新田

大気中の浮遊粉じんを抽集するエレットレット フィルターに大気中の臭気成分を吸着験去させる ハニカム型シート状般着剤を組合せた構造を特質 とする低圧力損失型の空気清浄機。

#### 発明の詳細な説明

この発明は大気中の砂じんと臭気成分を効率よ く除去する空気滑浄機に関するものであり、低い 比力損失、高い効率と高い安全性を特徴としてい る。

一般に室内や車内で使用されている空気滑浄機 は比較的低濃度の粉じんや臭気を効率良く除外す る為に、卵電式空気疣浄機或いは電気集じん機と 括性炭充てん層を組合せることにより、実用化さ れてきている。従来の鈴電報空気清浄機成いは電 気集じん器は含じん空気を適識させてコロナ紋電

により粉じん粒子を荷電させ、との粉じんを反対 軍艦又は電艦によりはさまれた形材で放去すると とを目的としている。このため、これらの装置は 数≧▽から数10≧▽ の高電圧を必要として、取扱 い上危険をともなりことが多く、高麗圧を必要と しない集じん装置が望まれている。高電圧を必要 としない巣じん袋世としては一般エアーフィルメ 一種材が使用されるが、盆内或いは草内空気の90 メ以上を占める 1.0 μ = 以下のサブミクロ粒子に 対して高い捕集効率を出すためには細いガラス線 維からできた密度の高い HRPA フイルターが使用 されねはならず、高い圧力損失に悩まされるとと になる。一方サブミクロンの粒子は何らかの質点 を所有していることは明らかであり、例えばメバ コの塩は正電荷をもつと言われている。その為、 高い捕集効率と低い圧力損失のあい矛盾する性能 を崩するためには、静能気力を利用して抽集する 新しいファクターがエアーフイルターに必要とな る。一方、空気中の臭気成分を厳去するために使 用されている粒状活性炭の充てん層は吸着速度だ

本発明は上記事情を重みてなされたものであり、 低圧力損失と高い除去率および高い安全性が保証 された空気滑浄機に関するものである。具体的に はエレクトレットフィルターにハニカム型のシー ト状設着剤を組合せた構造を特象としている。

エレクトレットフィルターはフィルターを構成する値材そのものが永久的に分価され、ある一定対の電荷を所有するものである。そのため、値材そのものに高麗圧をかけながら欲じんをおこなう
必要がなく、静電気力により、浄趣するサブミクロンの粒子を設着除去することが可能である。エレクトレットフィルターはエレクトレット化され

ム枠の中に入れ、熱固着して成型することも可能である。使用される粉末活性炭の粒径および繊維状态性炭の繊維径は小さいほど嵌着速度が速く好ましいが、砂粃時の経済性は反対に懸くなる。

以下、実施例により、本発明をさらに具体的に説明する。

#### 夹 庇 例

下記のエレクトレットフィルターとハニカム機シート状設滑材を組合せて空気滑浄機をつくり、 その性能を創定した。

風の上流個にエレクトレットフィルターを下流 個に設着剤を設置した。又比較として、エレクトレットされなかつたフィルター、BBPAフィルター、 及び粒状活性説の充てん事の仕様例も記載した。

(a) エレクトレットフイルター

材 寅 ポリプロピレン繊維

声 さ 6.0 =

目 付 ~200 / / ≥

压力损失 7= 160

捕業率 98%

ゆ ハニカム型シート状般着剤

材 質 磁維状活性炭

紙 仕 様 パルプ30%促抄紙、厚さ0.25= 目付501/2

段 加 工 ピッチ 3.1 = 、高さ2.0= 片段ポール

段ポール品を 長さ2.0 年に切断して積層

**正力損失 0.7= LO** 

③ エレクトレットされなかつたフィルター 材質、厚さ、目付はエレクトレットフィルターと同じ任力損失 7 = H<sub>\*</sub>O

储 製 孝 30≰

HEPA フィルター

材 質 ガラス繊維

厚 さ 0.6 ==

目 付 9 5 9 / ≥

· 諸 英 孝 98.5%

⑥ 粒状括性炭充てん層

材 質 粒状活性炭 4 - 6 メツシュ

赠 長 2 ㎝

**近力損失 15 = H₂0** 

いずれも風速は 50 m/eec. であり、 じん雑祭 単は大気じん中 0.5 μ = 以上 1.0 μ = 以下の粒子 げ μ およる効率である。

以上まとめると下板の第1枚のようになる。

第 1 表

	正力損失 (== H <sub>a</sub> O)	推 集 率
本発明(3)+(6)	7.7	9 8
比較量(() + (6)	7.7	3 0
@ + 6	170.7	9 '9
<b>0</b> + <b>0</b>	22.0	3.0
(d) + (e)	185	9 9

**^る。** そのた

4型シ

は住と

E 炭 が ;性 炭

, 紙用

加工 るし、 ニカ

501/2

第1 設からわかるように本発明の組合せによると極めて低い圧力損失で高い粉量効率をもつこと がほくわかる。

次に臭気成分の脱臭性について比較する。⑤と⑥について、オソン1 ppm での除去率を比較すると下記の第2数のようになり、本発明が脱臭性についてもすぐれていることがよくわかる。

第 2	表
	除去半乡
本発明①	9 5
比較例⑥	8 5